

Making slip from MFQ Plastic Clay.

You need:

- 1 10kg. pack of MFQ Plastic Clay.
- 1.75 litres Water.
- 3 gms Soda Ash.
- 10 gms Sodium Silicate.
- 7 gms Dispex added to 50mls water.
- Some method of mixing i.e. a small blunger.

Process:

1. Take a small amount of water and dissolve the Soda Ash and Sodium Silicate in it then add it back into the rest of the water.
2. Shred the MFQ and progressively add to water, a small amount at a time. Blunge until it is homogeneously mixed.
3. Slowly add the Dispex and water mix until you get the required slip density and viscosity.

Please note:

- As conditions vary from workshop to workshop it is recommended that comprehensive testing is undertaken to ensure the slip suits your requirements.