

FEATURES

WELSHPOOL, WESTERN AUSTRALIA

A ground smelter grade alumina consisting of several alumina phases, mainly delta and gamma. Milled predominantly finer than 45 microns. Typically used in ceramics and mild abrasive applications.

Calcined Alumina CA300 is tested and controlled to rigorous standards which ensure consistent chemical and physical properties resulting in predictable and repeatable performance. Unimin Australia actively manages a Quality Management System certified to ISO9001:2008.

The following properties may help you to determine the suitability of the product to best suit your application.

Welshpool CA300 (07/09)


CHEMICAL AND ANALYTICAL DATA

Mean Values. These Do Not Represent A Specification

Mean Percent by Weight		(UAL 8.5)	
Alumina	(Al ₂ O ₃)		95
Silica	(SiO ₂)		0.8
Soda	(Na ₂ O)		0.2
Lime	(CaO)		1.4
Ferric Oxide	(Fe ₂ O ₃)		<0.1
Loss on Ignition	(1000°C)	UAL 2.3	1.8
Specific Gravity		UAL2.13(b)	3.42
pH	(20% Slurry)	UAL2.11	10
Bulk Density (compacted)	(g/cm ³)	UAL 2.10(a)	1.2
Surface Area	(m ² /g)	UAL 2.8(c)	68
Powder Brightness	(R457nm)	UAL 2.1(e)	92

PARTICLE SIZE ANALYSIS

Mean Values. These Do Not Represent A Specification



ORDERING INFORMATION

Shipping Point:

Welshpool, Western Australia

Availability:

25 kg Multi-Wall Paper Bags

DISCLAIMER: Ranges and values of trial sample testing or on a Technical Information Sheet are typical or expected ranges and are not guaranteed ranges. You must satisfy yourself that the product is suitable for the purpose for which you intend to use it. Unimin makes no representations as to suitability, fitness or merchantability.

HAZARD WARNING: Avoid creating dust when handling, using or storing the product. Use only with adequate ventilation to keep exposure low. Undertake health and safety risk assessments on safe methods of handling and use appropriate to your workplace. To prevent inhalation of airborne dust, wear respiratory protection in accordance with Australian Standard AS1715 and AS1716. To prevent potential irritation to eyes, wear eye protection in accordance with Australian Standard AS1337.

Please refer to the relevant Unimin Australia Limited Material Safety Data Sheet (MSDS) for health hazard information before opening or using this product and take care when disposing of the empty bag/container (as it may contain product residue). If you do not have an MSDS, please ring the ACOHS 24 hour emergency phone number 1800 638 556 and you will be sent one.

FOR PRODUCT INFORMATION AND CUSTOMER SERVICE

AUST: Adelaide +61 8 8240 8200 Brisbane +61 7 3275 2499 Melbourne +61 3 9586 5400
 Sydney +61 2 9637 7066 Perth +61 8 9362 1411 Newcastle +61 2 4967 1222

NZ Auckland +64 9 914 7010 Visit our website www.unimin.com.au



UNIMIN AUSTRALIA LIMITED
 ACN 000 971 844