

Porcelainous clays.

	Clay	Filter	Bisque (Orton cones)	Glaze (Orton cones)	Characteristics
SP	Studio Porcelain				
JB1	Porcelain type	120#	012 to 06	7 to 10	White firing porcelain, possessing excellent plasticity and green strength, making it suitable for large objects, as well as, the most delicate pieces. JB1 can be fired as low as 1200°C but develops better strength at 1260°C to 1300°C.
WSP	White Porcelain	120#	5	8 to 9	An excellent white, porcelain style clay that offers a broad firing range. An extremely versatile body suitable for throwing, jigger jollying and pressing. The ideal body for high quality table ware.
LBSI	Southern Ice	120#	07 to 05	8 to 10	Truly magnificent, translucent, white porcelain. While it is one of the best porcelains available it is also surprisingly easy to work. For best whiteness and translucency fire in reduction. SOUTHERN ICE has received international recognition as one the world's best porcelain bodies and is now sold in Europe, UK, USA, NZ, Switzerland, France and Singapore.
LBSI PC	Southern Ice - Paper clay				

Notes:-

1. Unless otherwise specified the bodies are filter pressed, vacuum de-aired and packed as bags of approximately 10 kg weight, i.e. 100 bags to the tonne.
2. Conditions and production techniques vary widely from pottery to pottery; consequently, we strongly advise thorough evaluation and testing of any clay body to ensure its suitability.
3. Clayworks reserves the right to vary body specifications and composition, without notification.
4. The information provided is the latest available and supersedes all earlier publications.