

## Sculptural Clays.

		Filter	Bisque (Orton cones)	Glaze (Orton cones)	Characteristics
SF	Fine	30#	07 to 05	8 to 11	A body specifically designed for hand-building. It offers a broad firing range and fires to a beautiful sandstone colour. A wonderful RAKU body. A strong, robust body that stands up well when thrown.
SC	Coarse	16#	07 to 05	8 to 11	A version of SCULPTURAL FINE. Excellent for hand-building of large forms. Great in wood firings.
SW	Warm	30#	07 to 05	8 to 11	A version of Sculptural Fine with an addition of terracotta to give it a wonderful warm colour. Superb plastic qualities.
CBR	Buff Raku				
KAGERO	KAGERO				

### Notes:-

1. Unless otherwise specified the bodies are filter pressed, vacuum de-aired and packed as bags of approximately 10 kg weight, i.e. 100 bags to the tonne.
2. Conditions and production techniques vary widely from pottery to pottery; consequently, we strongly advise thorough evaluation and testing of any clay body to ensure its suitability.
3. Clayworks reserves the right to vary body specifications and composition, without notification.
4. The information provided is the latest available and supersedes all earlier publications.